AD A 101 299

# TECHNICAL LIBRARY

AD

TECHNICAL REPORT ARBRL-TR-02306

# DETERMINATION OF THE THERMAL DECOMPOSITION KINETICS OF POLYURETHANE FOAM BY GUGGENHEIM'S METHOD

Leon J. Decker
J. Richard Ward

March 1981

**US ARMY ARMAMENT RESEARCH AND DEVELOPMENT COMMAND**
**BALLISTIC RESEARCH LABORATORY**
ABERDEEN PROVING GROUND, MARYLAND

Approved for public release; distribution unlimited.

| REPORT DOCUMENTATION PAGE | | READ INSTRUCTIONS BEFORE COMPLETING FORM |
|---|---|---|
| 1. REPORT NUMBER<br><br>TECHNICAL REPORT ARBRL-TR-02306 | 2. GOVT ACCESSION NO. | 3. RECIPIENT'S CATALOG NUMBER |
| 4. TITLE (and Subtitle)<br><br>DETERMINATION OF THE THERMAL DECOMPOSITION KINETICS OF POLYURETHANE FOAM BY GUGGENHEIM'S METHOD | | 5. TYPE OF REPORT & PERIOD COVERED<br><br>BRL Technical Report |
| | | 6. PERFORMING ORG. REPORT NUMBER |
| 7. AUTHOR(s)<br><br>Leon J. Decker<br>J. Richard Ward | | 8. CONTRACT OR GRANT NUMBER(s) |
| 9. PERFORMING ORGANIZATION NAME AND ADDRESS<br>U.S. Army Ballistic Research Laboratory<br>ATTN: DRDAR-BLI<br>Aberdeen Proving Ground, MD 21005 | | 10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS<br><br>1L162618AH80 |
| 11. CONTROLLING OFFICE NAME AND ADDRESS<br>U.S. Army Armament Research & Development Command<br>U.S. Army Ballistic Research Laboratory<br>ATTN: DRDAR-BL<br>Aberdeen Proving Ground, MD 21005 | | 12. REPORT DATE<br><br>MARCH 1981 |
| | | 13. NUMBER OF PAGES<br>50 |
| 14. MONITORING AGENCY NAME & ADDRESS(if different from Controlling Office) | | 15. SECURITY CLASS. (of this report)<br><br>UNCLASSIFIED |
| | | 15a. DECLASSIFICATION/DOWNGRADING SCHEDULE |

16. DISTRIBUTION STATEMENT (of this Report)

Approved for public release; distribution unlimited.

17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)

18. SUPPLEMENTARY NOTES

19. KEY WORDS (Continue on reverse side if necessary and identify by block number)

Polyurethane Foam
Kinetics
Wear-Reducing Additive
Guggenheim's Method

20. ABSTRACT (Continue on reverse side if necessary and identify by block number) jmk

The kinetics of the thermal degradation of a rigid polyurethane foam used to reduce gun wear was determined to illustrate how Guggenheim's method could be applied to polymer decomposition. The polyurethane foam decomposed in two distinct steps. The first order activation parameters for each rate coefficient are $k_1 = 2.0 \times 10^{10} s^{-1} EXP(-134 kJ/mole/RT)$ and

$$k_2 = 1.2 \times 10^{10} s^{-1} EXP(-154 kJ/mole/RT).$$

# TABLE OF CONTENTS

Page

# LIST OF ILLUSTRATIONS

# LIST OF TABLES

7

# I. INTRODUCTION

The thermal decomposition rate of polyurethanes has long been of interest to polymer chemists in their endeavor to reduce the flammability of these widely used materials. A recent thesis reviews this history.[1]

Thermal decomposition of polyurethanes is also of interest in interior ballistics. Polyurethane mitigates barrel wear when a high-density polyurethane foam is glued to the inside wall of cartridge cases.[2,3] More recently propellants with polyurethane binders have demonstrated reduced sensitivity to accidental or uncontrolled ignition.[4] Wise has suggested the thermal decomposition of the binder governs the decreased vulnerability of the propellant.[5]

A common technique to measure the kinetics of the thermal decomposition is to monitor mass loss vs time at constant temperature ("isothermal"), or mass loss vs temperature at a constant heating rate ("dynamic"). The dynamic technique is experimentally convenient, since activation parameters can be determined in a single experiment. The isothermal technique, by contrast, requires rate coefficient determinations at several temperatures; the time for a reaction to go to completion is much longer than in a dynamic run; and the rate coefficient is sensitive to the value of mass selected at the end of the reaction. For polymers this choice can be arbitrary, since polymers typically decompose by consecutive reactions.

The experimental simplicity of the dynamic method prompted many investigators to apply this technique to polymer decomposition kinetics.[6]

---

[1] M.S. Ramakrishman, "Pyrolysis and Thermal Degradation of Rigid-Urethane Foams," Dept of Chemical Engineering, University of Utah, December 1975.

[2] L.A. Dickinson and D.E. McLennan, "Improvement of the Firing Accuracy and Cost Effectiveness of Guns Through the Use of Urethane Foams," J. Cellular Plastics, 1968, p 184.

[3] W. Joseph, "Use of Foamed Polyurethane in Decreasing Erosion," Picatinny Arsenal Technical Report No. 2520, June 1958.

[4] J.J. Rocchio and R.W. Deas, "Interior Ballistics of Nitramine - Inert Binder Formulations Being Evaluated for Low Vulnerability Propellants," 15th JANNAF Combustion Meeting Vol I, CPIA Publication 297, February 1979.

[5] S. Wise, BRL Report in preparation.

[6] J.H. Flynn, "The Historical Development of Applied Nonisothermal Kinetics", Thermal Analysis ed, R.F. Schmenker and P.D. Garn Vol 2, p 1111 (1969).

A number of investigators have questioned the validity of the dynamic method,[7-12] since rate coefficients determined isothermally did not agree with those determined with the dynamic method. MacCallum and Taylor go so far as to question the validity of the equations used in the dynamic method.[8]

In this report, the decomposition of a polyurethane is measured using Guggenheim's[13] method to evaluate the first-order rate coefficients. Guggenheim's technique seems particularly suited, since most polymers decompose by first-order kinetics[14,15] under an inert atmosphere, but the exact mass loss corresponding to the end of the reaction is difficult to discern for consecutive reactions.


## II. EXPERIMENTAL

Samples of polyurethane foam were cut from a piece of foam taken from a 105 mm M392A2 APDS round.[2,3] Polymer ingredients are given in Table 1.

---

[7] J.R. MacCallum and J. Tanner, "A Comparative Study of Some Methods of Assessing Kinetic Parameters from Thermogravimetric Analysis," *Euro Polymer J.*, 6, 907 (1970).

[8] J.R. MacCallum and J. Tanner, "Derivation of Rate Equations used in Thermogravimetry," *Nature*, 225, 1127 (1970).

[9] R.A.W. Hill, "Rate Equations in Thermogravimetry," *Nature*, 227, 703 (1970).

[10] R.M. Felder and E.P. Stahel, "Nonisothermal Chemical Kinetics," *Nature*, 228, (1970).

[11] E.L. Simmons and W.W. Wendlandt, "Nonisothermal Rate Equations," *Thermochimica Acta*, 3, 498 (1972).

[12] P.D. Garn, "Nonisothermal Kinetics," *J. Thermal Analysis*, 6 237 (1974).

[13] F. Daniels, *Experimental Physical Chemistry*, 6th ed. New York, McGraw-Hill Book Co. Inc. 1962, p 140.

[14] L.P. Rumao and K.C. Frisch, "Thermal Degradation of Polyurethanes Based on Xylxylene Dusocyamates," *J. Polymer Science*, A-1, 10, 1499 (1972).

[15] E. Dyer and R.J. Hammond, "Thermal Degradation of N-Substituted Polycarbamates," *J. Polymer Sci: Part A*, 2, 1 (1964).

TABLE 1.    COMPOSITION OF POLYURETHANE FOAM

| Resin Prepolymer Ingredients | Parts by Weight |
|---|---|
| polyethylene glycol 200 | 10.5 |
| polypropylene glycol 1200 | 6.5 |
| castor oil | 36.5 |
| 2,4 toluene diisocyanate | 46.5 |

| Catalyst Mixture Ingredients | Parts by Weight* |
|---|---|
| polypropylene glycol | 10.0 |
| glycerine | 7.5 |
| polyethylene glycol | 3.75 |
| ferric acetylacetonate | 0.15 |
| nigrosine black | 0.25 |
| dibutyltin dilaurate | 0.30 |

*Remainder of foam is resin.*

Thermogravimetric measurements were made on a DuPont Model 950 thermogravimetric analyzer in a flowing, helium atmosphere (100 ml/min). Procedures for isothermal kinetic runs have been described in an earlier report.[16]

Guggenheim's method may be illustrated with the integrated form of the differential equation for a first-order reaction given below:

$$m_t - m_\infty = (m_0 - m_\infty) e^{-kt} , \tag{1}$$

where $m_t$ = mass at time, t,

$m_\infty$ = mass at completion of reaction,

$m_0$ = initial mass,

$k$ = first-order rate coefficient, and

$t$ = time.

[16] J.R. Ward, "Kinetics of Talc Dehydroxylation," BRL Memorandum Report No. 2393, June 1974.    (AD #784083)

At time, $t + \Delta t$, equation (1) becomes

$$m_{(t+\Delta t)} = m_\infty + (m_0 - m_\infty)\, e^{-k(t+\Delta t)} \ . \tag{2}$$

Subtracting equation (2) from (1) gives

$$m_t - m_{(t+\Delta t)} = (m_0 - m_\infty)\, e^{-kt}(1 - e^{-k\Delta t}) \ . \tag{3}$$

Taking logs of both sides of (3) produces

$$\ln(m_t - m_{(t+\Delta t)}) = -kt + \ln((m_0 - m_\infty)(1 - e^{-k\Delta t})) \ . \tag{4}$$

A plot of $\ln(m_t - m_{(t+\Delta t)})$ vs $t$ will give a straight line with slope, $-k$. In the experiments reported here, the readings, R, from the heating curve are used to get the rate coefficient.

## III. RESULTS AND DISCUSSION

The polyurethane foam decomposes in two distinct steps with maximum decomposition rates at 558K and 673K. Rate coefficients were determined for each decomposition region by making isothermal TG runs within each region. Appendix A lists the data for the low-temperature region experiments, while Appendix B lists the data for the high-temperature region experiments. In all kinetic runs, the y-axis displacement was 2.0 mg/division. The rate coefficients were determined directly from the y-axis displacements.

Tables 2 and 3 summarize the rate coefficients determined from plots of $\ln(R_t - R_{(t+\Delta t)})$ vs $t$, where R is the reading from the TG curve.

Figures 1 and 2 illustrate plots of $\ln k$ vs $1/T$. The activation energy, $E_a$, and the pre-exponential, A, were determined from a linear least-squares fit of the rate coefficients in Tables 2 and 3 to

$$\ln k = \ln A - E_a/RT \ . \tag{5}$$

12

TABLE 2. RATE COEFFICIENTS FOR LOW-TEMPERATURE REACTION

| Run I.D. | mass,mg | T, K | $\Delta t, s, \times 10^{-3}$ | $k, s^{-1}, \times 10^{3}$ |
|---|---|---|---|---|
| 3-12/16 | 25.83 | 472 | 36 | 0.036 |
| 1-12/29 | 22.80 | 476 | 36 | .031 |
| 1-12/28 | 20.56 | 477 | 36 | .033 |
| 2-12/16 | 23.29 | 504 | 3.6 | .26 |
| 1-12/16 | 24.54 | 504 | 3.6 | .25 |
| 2-12/3 | 17.77 | 533 | 0.42 | 1.6 |
| 3-12/3 | 18.99 | 533 | .42 | 1.7 |
| 1-12/3 | 25.68 | 559 | .18 | 5.8 |
| 1-12/2 | 23.79 | 560 | .18 | 4.4 |

13

TABLE 3. RATE COEFFICIENTS FOR HIGH-TEMPERATURE REACTION

| Run ID | mass,mg | T, K | $\Delta t,s,$ | $k,s^{-1},\times10^3$ |
|--------|---------|------|------|------|
| 1-1/14 | 21.20 | 593 | 3,600 | 0.28 |
| 1-1/13 | 17.91 | 593 | 3,600 | .29 |
| 1-1/12 | 15.08 | 593 | 3,600 | .29 |
| 1-1/11 | 20.57 | 594 | 3,600 | .29 |
| 1-11/23 | 18.23 | 617 | 1,800 | .91 |
| 1-11/24 | 20.29 | 618 | 1,800 | 1.0 |
| 1-11/26 | 17.50 | 636 | 600 | 2.3 |
| 2-11/26 | 18.00 | 643 | 600 | 3.2 |
| 3-11/26 | 22.76 | 670 | 300 | 12.3 |
| 4-11/26 | 18.31 | 670 | 300 | 11.8 |

Figure 1.   Low-Temperature Rate Coefficient <u>vs</u>.
Reciprocal Absolute Temperature

Figure 2.   High-Temperature Rate Coefficient <u>vs</u>.
            Reciprocal Absolute Temperature

The results of these calculations are shown below. The error corresponds to the sample standard deviation.

| | $E_a$, kJ/RT/mole | $\ln A, s^{-1}$ |
|---|---|---|
| $k_1$ | 134±5 | 23.7±1 |
| $k_2$ | 154±2 | 23.2±0.04 |

## IV. CONCLUSION

The kinetics of the thermal degradation of a rigid polyurethane foam used to reduce gun wear was determined to illustrate how Guggenheim's method could be applied to polymer decomposition. The polyurethane foam decomposed in two distinct steps. The first-order activation parameters for each rate coefficient are $k_1 = 2.0 \times 10^{10} s^{-1} EXP(-134 kJ/mole/RT)$ and $k_2 = 1.2 \times 10^{10} s^{-1} EXP(-154 kJ/mole/RT)$, respectively.

# REFERENCES

1. M.S. Ramakrishnan, "Pyrolysis and Thermal Degradation of Rigid-Urethane Foams," Dept of Chemical Engineering, University of Utah, December 1975.

2. L.A. Dickinson and D.E. McLennan, "Improvement of the Firing Accuracy and Cost Effectiveness of Guns Through the Use of Urethane Foams," J. Cellular Plastics, 1968, 184.

3. W. Joseph, "Use of Foamed Polyurethane in Decreasing Erosion," Picatinny Arsenal Technical Report No. 2520, June 1958.

4. J.J. Rocchio and R.W. Deas, "Interior Ballistics of Nitramine-Inert Binder Formulations Being Evaluated for Low Vulnerability Propellant," 15th JANNAF Combustion Meeting Vol I, CPIA Publication 297, February 1979.

5. S. Wise, BRL Report in preparation.

6. J.H. Flynn, "The Historical Development of Applied Nonisothermal Kinetics," Thermal Analysis ed, R.F. Schumenker and P.D. Garn Vol 2, 1111 (1969).

7. J.R. MacCallum and J. Tanner, "A Comparative Study of Some Methods of Assessing Kinetic Parameters from Thermogravimetric Analysis," Euro. Polymer J., 6, 907 (1970).

8. J.R. MacCallum and J. Tanner, "Derivation of Rate Equations used in Thermogravimetry." Nature, 225, 1127 (1970).

9. R.A.W. Hill, "Rate Equations in Thermogravimetry," Nature, 227, 703 (1970).

10. R.M. Felder and E.P. Stahel, "Nonisothermal Chemical Kinetics," Nature, 228, (1970).

11. E.L. Simmons and W.W. Wendlandt, "Nonisothermal Rate Equations," Thermochimica Acta, 3, 498 (1972).

12. P.D. Garn, "Nonisothermal Kinetics," J. Thermal Analysis, 6 237 (1974).

13. F. Daniels, Experimental Physical Chemistry 6th ed. New York, McGraw-Hill Book Co. Inc. 1962, p 140.

14. L.P. Rumao and K.C. Frisch, "Thermal Degradation of Polyurethanes Based on Xylxylene Dusocyamates," J. Polymer Science, A-1, 10, 1499 (1972).

REFERENCES (continued)

15. E. Dyer and R.J. Hammond, "Thermal Degradation of N-Substituted Polycarbamates," J. Polymer Sci: Part A, 2, 1 (1964).

16. J.R. Ward, "Kinetics of Talc Dehydroxylation," BRL Memorandum Report No. 2393, June 1974. (AD #784083)

APPENDIX A

Readings from Isothermal TG Curve
for Low-Temperature Decomposition (1 div = 2 mg)

Run ID            3-12/16
mass, mg          25.83
T, K              472
$\Delta t$, min   600

| $R_t$ | $R_{(t+\Delta t)}$ | t, min |
|-------|--------------------|--------|
| 7.42  | 5.24               | 50     |
| 7.16  | 5.16               | 100    |
| 6.92  | 5.09               | 150    |
| 6.66  | 5.02               | 200    |
| 6.41  | 4.97               | 250    |
| 6.21  | 4.91               | 300    |
| 6.01  | 4.86               | 350    |
| 5.84  | 4.80               | 400    |

Run ID        1-12/29
mass, mg     22.80
T, K         476
Δt, min      600

| $R_t$ | $R_{(t+\Delta t)}$ | t, min |
|-------|--------------------|--------|
| 7.84  | 5.89               | 10     |
| 7.80  | 5.87               | 20     |
| 7.73  | 5.84               | 35     |
| 7.68  | 5.81               | 50     |
| 7.45  | 5.74               | 100    |
| 7.25  | 5.68               | 150    |
| 7.05  | 5.61               | 200    |
| 6.85  | 5.55               | 250    |
| 6.67  | 5.49               | 300    |
| 6.50  | 5.44               | 350    |
| 6.36  | 5.39               | 400    |
| 6.22  | 5.34               | 450    |
| 6.10  | 5.30               | 500    |

Run ID          1-12/28
mass, mg        20.56
T, K            477
Δt, min         600

| $R_t$ | $R_{(t+\Delta t)}$ | t, min |
|------|------|------|
| 7.73 | 5.89 | 10 |
| 7.69 | 5.88 | 20 |
| 7.62 | 5.84 | 35 |
| 7.56 | 5.81 | 50 |
| 7.34 | 5.74 | 100 |
| 7.15 | 5.68 | 150 |
| 6.97 | 5.62 | 200 |
| 6.77 | 5.58 | 250 |
| 6.60 | 5.52 | 300 |
| 6.44 | 5.48 | 350 |
| 6.31 | 5.43 | 400 |
| 6.19 | 5.38 | 450 |
| 6.08 | 5.36 | 500 |

```
Run ID          2-12/16
mass, mg        23.29
T, K            504
Δt, min          60
```

| $R_t$ | $R_{(t+\Delta t)}$ | t, min |
|-------|---------------------|--------|
| 7.41  | 5.49                | 5      |
| 7.19  | 5.39                | 10     |
| 6.98  | 5.29                | 15     |
| 6.77  | 5.22                | 20     |
| 6.57  | 5.14                | 25     |
| 6.39  | 5.08                | 30     |
| 6.23  | 5.02                | 35     |
| 6.07  | 4.97                | 40     |
| 5.93  | 4.91                | 45     |
| 5.80  | 4.86                | 50     |
| 5.68  | 4.81                | 55     |
| 5.59  | 4.77                | 60     |
| 5.49  | 4.73                | 65     |
| 5.39  | 4.69                | 70     |

| Run ID | 1-12/16 |
|---|---|
| mass, mg | 24.54 |
| T, K | 504 |
| $\Delta t$, min | 60 |

| $R_t$ | $R_{(t+\Delta t)}$ | t, min |
|---|---|---|
| 7.29 | 5.19 | 5 |
| 7.05 | 5.07 | 10 |
| 6.82 | 4.98 | 15 |
| 6.61 | 4.90 | 20 |
| 6.39 | 4.82 | 25 |
| 6.20 | 4.75 | 30 |
| 6.01 | 4.68 | 35 |
| 5.85 | 4.61 | 40 |
| 5.69 | 4.54 | 50 |
| 5.55 | 4.48 | 55 |
| 5.41 | 4.42 | 60 |
| 5.29 | 4.38 | 65 |
| 5.19 | 4.33 | 70 |

Run ID          2-12/3
mass, mg        17.77
T, K            533
Δt, min         7

| $R_t$ | $R_{(t+\Delta t)}$ | t, min |
|------|------|------|
| 8.00 | 6.77 | 1.25 |
| 7.85 | 6.55 | 2.0 |
| 7.65 | 6.42 | 3.0 |
| 7.42 | 6.30 | 4.0 |
| 7.23 | 6.20 | 5.0 |
| 7.05 | 6.09 | 6.0 |
| 6.88 | 5.99 | 7.0 |
| 6.71 | 5.91 | 8.0 |
| 6.55 | 5.84 | 9.0 |
| 6.42 | 5.77 | 10.0 |
| 6.30 | 5.71 | 11.0 |
| 6.20 | 5.66 | 12.0 |
| 6.09 | 5.61 | 13.0 |
| 5.99 | 5.56 | 14.0 |
| 5.91 | 5.51 | 15.0 |
| 5.84 | 5.47 | 16.0 |

Run ID          3-12/3
mass, mg        18.99
T, K            533
$\Delta t$, min   7

| $R_t$ | $R_{(t+\Delta t)}$ | t, min |
|-------|--------------------|--------|
| 6.20 | 7.59 | 1.0 |
| 6.11 | 7.47 | 1.5 |
| 6.01 | 7.36 | 2.0 |
| 5.85 | 7.16 | 3.0 |
| 5.71 | 6.97 | 4.0 |
| 5.57 | 6.76 | 5.0 |
| 5.48 | 6.56 | 6.0 |
| 5.37 | 6.38 | 7.0 |
| 5.29 | 6.20 | 8.0 |
| 5.20 | 6.01 | 9.0 |
| 5.13 | 5.85 | 10.0 |
| 4.94 | 5.48 | 13.0 |
| 4.84 | 5.29 | 15.0 |

Run ID          1-12/3
mass, mg        25.68
T, K            559
$\Delta t$, min     3

| $R_t$ | $R_{(t+\Delta t)}$ | t, min |
|------|------|------|
| 6.39 | 4.20 | 2 |
| 5.28 | 3.89 | 3 |
| 4.61 | 3.66 | 4 |
| 4.20 | 3.51 | 5 |
| 3.89 | 3.37 | 6 |
| 3.66 | 3.24 | 7 |

| Run ID | 1-12/2 |
|--------|--------|
| mass, mg | 23.79 |
| T, K | 560 |
| $\Delta t$, min | 3 |

| $R_t$ | $R_{(t+\Delta t)}$ | t, min |
|-------|--------------------|--------|
| 7.46 | 5.10 | 1.5 |
| 7.07 | 4.86 | 2.0 |
| 6.14 | 4.45 | 3.0 |
| 5.39 | 4.15 | 4.0 |
| 4.86 | 3.90 | 5.0 |
| 4.45 | 3.70 | 6.0 |
| 4.15 | 3.55 | 7.0 |
| 3.90 | 3.41 | 8.0 |
| 3.55 | 3.30 | 10.0 |

APPENDIX B

Readings from Isothermal TG Curve
for High-Temperature Decomposition (1 div = 2 mg)

Run ID          1-1/14
mass, mg        21.20
T, K            593
Δt, min         60

| $R_t$ | $R_{(t+\Delta t)}$ | t, min |
|-------|-------------------|--------|
| 3.61  | 5.07              | 10     |
| 3.50  | 4.69              | 20     |
| 3.39  | 4.39              | 30     |
| 3.29  | 4.15              | 40     |
| 3.20  | 3.94              | 50     |

```
Run ID          1-1/13
mass, mg        17.91
T, K            593
Δt, min         60
```

| $R_t$ | $R_{(t+\Delta t)}$ | t, min |
|-------|--------------------|--------|
| 3.65  | 4.90               | 10     |
| 3.54  | 4.57               | 20     |
| 3.46  | 4.31               | 30     |
| 3.37  | 4.11               | 40     |
| 3.30  | 3.94               | 50     |

Run ID            1-1/12
mass, mg          15.08
T, K              593
$\Delta t$, min   60

| $R_t$ | $R_{(t+\Delta t)}$ | t, min |
|-------|--------------------|--------|
| 3.87  | 2.78               | 10     |
| 3.59  | 2.70               | 20     |
| 3.38  | 2.62               | 30     |
| 3.18  | 2.54               | 40     |
| 3.01  | 2.48               | 50     |

```
Run Id            1-1/11
mass, mg          20.57
T, K              594
Δt, min           60
```

| $R_t$ | $R_{(t+\Delta t)}$ | t, min |
|-------|--------------------|--------|
| 5.28  | 3.74               | 10     |
| 4.89  | 3.61               | 20     |
| 4.57  | 3.50               | 30     |
| 4.31  | 3.40               | 40     |
| 4.10  | 3.33               | 50     |
| 3.90  | 3.26               | 60     |

```
Run ID          1-11/23
mass, mg        18.23
T, K            617
Δt, min         30
```

| $R_t$ | $R_{(t+\Delta t)}$ | t, min |
|------|------|------|
| 6.54 | 2.97 | 1.0 |
| 6.02 | 2.97 | 1.2 |
| 5.70 | 2.96 | 1.4 |
| 5.53 | 2.96 | 1.6 |
| 5.41 | 2.95 | 1.8 |
| 5.32 | 2.95 | 2.0 |
| 5.18 | 2.94 | 2.5 |
| 5.08 | 2.92 | 3.0 |
| 4.91 | 2.90 | 4.0 |
| 4.77 | 2.88 | 5.0 |
| 4.60 | 2.85 | 6.0 |
| 4.48 | 2.83 | 7.0 |
| 4.35 | 2.81 | 8.0 |
| 4.24 | 2.79 | 9.0 |
| 4.16 | 2.78 | 10.0 |
| 3.72 | 2.70 | 15.0 |
| 3.41 | 2.61 | 20.0 |

Run ID          1-11/24
mass, mg        20.29
T, K            618
Δt, min         30

| $R_t$ | $R_{(t+\Delta t)}$ | t, min |
|-------|--------------------|--------|
| 7.20  | 2.93               | 1.1    |
| 6.90  | 2.93               | 1.2    |
| 6.65  | 2.92               | 1.3    |
| 6.45  | 2.92               | 1.4    |
| 6.17  | 2.92               | 1.6    |
| 5.96  | 2.91               | 1.8    |
| 5.83  | 2.90               | 2.0    |
| 5.46  | 2.87               | 3.0    |
| 5.26  | 2.84               | 4.0    |
| 5.05  | 2.82               | 5.0    |
| 4.89  | 2.79               | 6.0    |
| 4.60  | 2.74               | 8.0    |
| 4.36  | 2.70               | 10.0   |
| 4.09  | 2.63               | 12.5   |
| 3.81  | 2.60               | 15.0   |
| 3.49  | 2.56               | 20     |
| 3.20  | 2.49               | 25     |
| 2.98  | 2.42               | 30     |
| 3.82  | 2.39               | 35     |

Run ID          1-1/17
mass, mg        19.80
T, K            623
Δt, min         30

| $R_t$ | $R_{(t+\Delta t)}$ | t, min |
|-------|--------------------|--------|
| 4.67  | 2.68               | 5.0    |
| 4.34  | 2.62               | 7.5    |
| 4.06  | 2.56               | 10.0   |
| 3.81  | 2.50               | 12.5   |
| 3.60  | 2.46               | 15.0   |
| 3.43  | 2.40               | 17.5   |
| 3.27  | 2.36               | 20.0   |
| 3.13  | 2.32               | 22.5   |
| 3.01  | 2.29               | 25.0   |
| 2.82  | 2.22               | 30.0   |

Run ID          1-1/18
mass, mg        15.32
T, K            624
$\Delta t$, min        30


$R_t$          $R_{(t+\Delta t)}$          t, min

3.68          2,11          5

3.18          2.02          10

2.82          1.95          15

2.57          1.88          20

2.37          1.80          25

```
Run ID          1-11/26
mass, mg        17.50
T, K            636
Δt, min         10
```

| $R_t$ | $R_{(t+\Delta t)}$ | t, min |
|-------|--------------------|--------|
| 4.23  | 2.22               | 2.0    |
| 3.57  | 2.09               | 4.0    |
| 3.07  | 1.98               | 6.0    |
| 2.71  | 1.90               | 8.0    |
| 2.43  | 1.83               | 10.0   |
| 2.02  | 1.71               | 15.0   |
| 1.83  | 1.65               | 20.0   |
| 1.71  | 1.60               | 25.0   |
| 1.65  | 1.58               | 30.0   |

| Run ID | 2-11/26 |
|---|---|
| mass, mg | 18.00 |
| T, K | 643 |
| $\Delta t$, min | 10 |

| $R_t$ | $R_{(t+\Delta t)}$ | t, min |
|---|---|---|
| 5.04 | 2.37 | 1.2 |
| 4.78 | 2.33 | 1.6 |
| 4.58 | 2.30 | 2.0 |
| 4.35 | 2.27 | 2.5 |
| 4.15 | 2.23 | 3.0 |
| 3.77 | 2.18 | 4.0 |
| 3.46 | 2.13 | 5.0 |
| 3.20 | 2.10 | 6.0 |
| 2.97 | 2.07 | 7.0 |
| 2.78 | 2.04 | 8.0 |
| 2.62 | 2.02 | 9.0 |
| 2.50 | 2.00 | 10.0 |
| 2.39 | 1.99 | 11.0 |

| Run ID | 3-11/26 |
|---|---|
| mass, mg | 22.76 |
| T, K | 670 |
| $\Delta t$, min | 5 |

| $R_t$ | t, min | $R_{(t+\Delta t)}$ |
|---|---|---|
| 4.12 | 1.0 | 0.56 |
| 3.72 | 1.2 | .55 |
| 3.37 | 1.4 | .54 |
| 3.02 | 1.6 | .53 |
| 2.70 | 1.8 | .52 |
| 2.41 | 2.0 | .51 |
| 1.39 | 3.0 | .47 |
| 0.86 | 4.0 | .42 |
| .64 | 5.0 | .37 |

Run ID          4-11/26
mass, mg        18.31
T, K            670
Δt, min         5

| $R_t$ | $R_{(t+\Delta t)}$ | Δt, min |
|------|------|------|
| 4.40 | 1.52 | 1.0 |
| 4.09 | 1.51 | 1.2 |
| 3.76 | 1.50 | 1.4 |
| 3.47 | 1.49 | 1.6 |
| 3.21 | 1.48 | 1.8 |
| 2.97 | 1.48 | 2.0 |
| 2.77 | 1.47 | 2.2 |
| 2.59 | 1.46 | 2.4 |
| 2.42 | 1.45 | 2.6 |
| 2.28 | 1.45 | 2.8 |
| 2.16 | 1.45 | 3.0 |
| 1.94 | 1.42 | 3.5 |
| 1.77 | 1.40 | 4.0 |
| 1.64 | 1.39 | 4.5 |
| 1.58 | 1.38 | 5.0 |

| No. of Copies | Organization |
|---|---|
| 12 | Commander<br>Defense Technical Info Center<br>ATTN: DDC-DDA<br>Cameron Station<br>Alexandria, VA 22314 |
| 1 | Director of Defense Research<br>and Engineering<br>ATTN: R. Thorkildsen<br>The Pentagon<br>Washington, DC 20301 |
| 1 | Director<br>Defense Advanced Research<br>Projects Agency<br>Director, Materials Division<br>1400 Wilson Boulevard<br>Arlington, VA 22209 |
| 3 | HQDA (DAMA-ARZ; DAMA-CSM;<br>DAMA-WSW)<br>Washington, DC 20301 |
| 1 | Commander<br>US Army Materiel Development<br>and Readiness Command<br>ATTN: DRCDMD-ST<br>5001 Eisenhower Avenue<br>Alexandria, VA 22333 |
| 2 | Commander<br>US Army Armament Research<br>and Development Command<br>ATTN: DRDAR-TSS<br>Dover, NJ 07801 |
| 5 | Commander<br>US Army Armament Research<br>and Development Command<br>ATTN: FC & SCWSL, D. Gyorog<br>H. Kahn<br>B. Brodman<br>S. Cytron<br>T. Hung<br>Dover, NJ 07801 |

| No. of Copies | Organization |
|---|---|
| 6 | Commander<br>US Army Armament Research &<br>Development Command<br>ATTN: DRDAR-LC, J. Frasier<br>H. Fair<br>J. Lannon<br>A. Bracuti<br>A. Moss<br>R. Walker<br>Dover, NJ 07801 |
| 6 | Commander<br>US Army Armament Research &<br>Development Command<br>ATTN: DRDAR-LC, J. Picard<br>D. Costa<br>E. Barrieres<br>R. Corn<br>K. Rubin<br>J. Houle<br>Dover, NJ 07801 |
| 4 | Commander<br>US Army Armament Research &<br>Development Command<br>ATTN: DRDAR-LC, E. Wurzel<br>K. Russell<br>D. Downs<br>R.L. Trask<br>Dover, NJ 07801 |
| 1 | Commander<br>US Army Armament Research &<br>Development Command<br>ATTN: DRDAR-QA, J. Rutkowski<br>Dover, NJ 07801 |
| 1 | Commander<br>US Army Armament Materiel<br>Readiness Command<br>ATTN: DRSAR-LEP-L, Tech Lib<br>Rock Island, IL 61299 |

# DISTRIBUTION LIST

| No. of Copies | Organization | No. of Copies | Organization |
|---|---|---|---|
| 5 | Commander<br>US Army Armament Research<br>and Development Command<br>Benet Weapons Laboratory<br>ATTN:   I. Ahmad<br>         T. Davidson<br>         J. Zweig<br>         G. Friar<br>         DRDAR-LCB-TL<br>Watervliet, NY  12189 | 1 | Commander<br>US Army Electronics Research<br>and Development Command<br>Technical Support Activity<br>ATTN:   DELSD-L<br>Fort Monmouth, NJ  07703 |
| 5 | Commander<br>US Army Armament Research<br>and Development Command<br>Benet Weapons Laboratory<br>ATTN:   J. Busuttil<br>         W. Austin<br>         R. Montgomery<br>         R. Billington<br>         J. Santini<br>Watervliet, NY  12189 | 1 | Commander<br>US Army Missile Command<br>ATTN:   DRSMI-R<br>Redstone Arsenal, AL  35809 |
| | | 1 | Commander<br>US Army Missile Command<br>ATTN:   DRSMI-YDL<br>Redstone Arsenal, AL  35809 |
| 1 | Commander<br>US Army Aviation Research<br>and Development Command<br>ATTN:   DRSAV-E<br>P. O. Box 209<br>St. Louis, MO  63166 | 1 | Commander<br>US Army Tank Automotive<br>Research & Development Cmd<br>ATTN:   DRDTA-UL<br>Warren, MI  48090 |
| 1 | Director<br>US Army Air Mobility Research<br>and Development Laboratory<br>Ames Research Center<br>Moffett Field, CA  94035 | 1 | President<br>US Army Armor & Engineer Bd<br>Fort Knox, KY  40121 |
| | | 1 | Project Manager, M60 Tanks<br>US Army Tank & Automotive Cmd<br>28150 Dequindre Road<br>Warren, MI  48090 |
| 1 | Commander<br>US Army Research & Technology<br>Laboratories<br>ATTN:   R. A. Langsworthy<br>Fort Eustis, VA  23604 | 4 | Project Manager<br>Cannon Artillery Wpns Sys<br>ATTN:   DRCPM-CAWS<br>US Army ARRADCOM<br>Dover, NJ  07801 |
| 1 | Commander<br>US Army Communications Rsch<br>and Development Command<br>ATTN:   DRDCO-PPA-SA<br>Fort Monmouth, NJ  07703 | 2 | Project Manager - M110E2<br>ATTN:   J. Turkeltaub<br>         S. Smith<br>Rock Island, IL  61299 |

# DISTRIBUTION LIST

| No. of Copies | Organization | No. of Copies | Organization |
|---|---|---|---|
| 1 | Project Manager - XM1 Tank<br>US Army Tank Automotive<br>Development Command<br>28150 Dequindre Road<br>Warren, MI 48090 | 1 | Commander<br>US Army Armor Center<br>ATTN: ATZK-XM1<br>Fort Knox, KY 40121 |
| 1 | Project Manager - XM1<br>Tank Main Armament Dev Div<br>Dover, NJ 07801 | 1 | Commander<br>US Army Field Artillery School<br>ATTN: J. Porter<br>Fort Sill, OK 73503 |
| 1 | Project Manager - ARGADS<br>Dover, NJ 07801 | 5 | Commander<br>Naval Surface Weapons Center<br>ATTN: M. Shamblen<br>J. O'Brasky<br>C. Smith<br>L. Russell<br>T. W. Smith<br>Dahlgren, VA 22448 |
| 1 | Commander<br>US Army DARCOM Materiel<br>Readiness Support Activity<br>Lexington, KY 40511 | | |
| 2 | Director<br>US Army Materials and<br>Mechanics Research Center<br>ATTN: J. W. Johnson<br>K. Shepard<br>Watertown, MA 02172 | 2 | Commander<br>Naval Ordnance Station<br>ATTN: L. Dickinson<br>S. Mitchell<br>Indian Head, MD 20640 |
| 3 | Director<br>US Army Research Office<br>ATTN: P. Parrish<br>E. Saibel<br>D. Squire<br>P. O. Box 12211<br>Research Triangle Park<br>NC 27709 | 1 | Commander<br>Naval Ordnance Station,<br>Louisville<br>ATTN: F. Blume<br>Louisville, KY 40202 |
| | | 2 | AFATL (D. Uhrig, O. Heiney)<br>Eglin AFB, FL 32542 |
| 1 | Director<br>US Army TRADOC Systems<br>Analysis Activity<br>ATTN: ATAA-SL, Tech Lib<br>White Sands Missile Range<br>NM 88002 | 1 | National Bureau of Standards<br>Materials Divison<br>ATTN: A. W. Ruff<br>Washington, DC 20234 |
| | | 1 | National Science Foundation<br>Materials Division<br>Washington, DC 20550 |
| 1 | Commander<br>US Army Air Defense Center<br>ATTN: ATSA-SM-L<br>Fort Bliss, TX 79916 | 1 | Battelle Columbus Laboratory<br>ATTN: G. Wolken<br>Columbus, OH 43201 |

DISTRIBUTION LIST

No. of
Copies        Organization

1   Director
    Lawrence Livermore Laboratory
    ATTN:  J. Kury
    Livermore, CA  94550

2   Calspan Corporation
    ATTN:  G. Sterbutzel
           F. Vassallo
    P. O. Box 400
    Buffalo, NY  14221

1   Director
    Chemical Propulsion Info Agcy
    Johns Hopkins University
    ATTN:  T. Christian
    Johns Hopkins Road
    Laurel, MD  20810

1   Princeton University
    Forrestal Campus Library
    ATTN:  Tech Lib
           B. Royce
    P. O. Box 710
    Princeton, NJ  08540

1   Purdue University
    School of Mechanical Eng
    ATTN:  J. R. Osborn
    W. Lafayette, IN  47909

No. of
Copies          Organization

1   SRI International
    Materials Research Center
    333 Ravenswood Avenue
    Menlo Park, CA  94025

1   University of Illinois
    Dept of Aeronautics and
       Aerospace Engineering
    ATTN:  H. Krier
    Urbana, IL  61803

Aberdeen Proving Ground

    Dir, USAMTD
      ATTN:  H. Graves, Bldg. 400
             L. Barnhardt, Bldg. 400
             K. Jones, Bldg. 400
             R. Moody, Bldg. 400
    Cdr, USATECOM
      ATTN:  DRSTE-FA
             DRSTE-AR
             DRSTE-AD
             DRSTE-TO-F
    Dir, USAMSAA
      ATTN:  DRXSY-D
             DRXSY-MP, H. Cohen
             D. Barnhardt, RAM Div
             G. Alexander, RAM Div
             Air Warfare Div
             Ground Warfare Div
             RAM Division
    Dir, USACSL, Bldg. E3516
      ATTN:  DRDAR-CLB-PA

50

## USER EVALUATION OF REPORT

Please take a few minutes to answer the questions below; tear out this sheet, fold as indicated, staple or tape closed, and place in the mail. Your comments will provide us with information for improving future reports.

1. BRL Report Number_____

2. Does this report satisfy a need? (Comment on purpose, related project, or other area of interest for which report will be used.)

_____

_____

_____

3. How, specifically, is the report being used? (Information source, design data or procedure, management procedure, source of ideas, etc.)_____

_____

_____

4. Has the information in this report led to any quantitative savings as far as man-hours/contract dollars saved, operating costs avoided, efficiencies achieved, etc.? If so, please elaborate.

_____

_____

5. General Comments (Indicate what you think should be changed to make this report and future reports of this type more responsive to your needs, more usable, improve readability, etc.)_____

_____

_____

_____

6. If you would like to be contacted by the personnel who prepared this report to raise specific questions or discuss the topic, please fill in the following information.

Name:_____

Telephone Number:_____

Organization Address:_____

_____

_____